



3770 Embassy Parkway Akron, Ohio 44333
330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

ELASTOMERS
-NITRILE-

APCOFLEX® NX146
Carboxylated Nitrile Rubber

PRODUCT DESCRIPTION:

Apcoflex NX146 is a copolymer of butadiene and acrylonitrile manufactured by advanced cold emulsion polymerization and modified with carboxylic acid. It is a non-staining, medium mooney, and medium acrylonitrile polymer. Apcoflex NX146 offers excellent tensile strength and abrasion properties in addition to typical nitrile characteristics of resistance to most fuels, solvents, oils, and gas permeation.

TYPICAL PROPERTIES:

Appearance	Tan
Specific Gravity, gm/cc	0.99
Mooney Viscosity, ML (1+4) @100°C	45
Bound ACN, Content	32.5
Stabilizer.....	Non-Staining

APPLICATION:

Apcoflex NX146 is recommended for use in products such as printing rolls, conveyor belts, hose covers, oil well drilling parts, footwear components, textile cots and aprons.

PACKAGE AND FORM: 55.0 and 77.0 lb. bale

STORAGE:

Store in original packaging away from direct sunlight and sources of heat.

rh 3/17
x-Apcoflex NX146

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.