



3770 Embassy Parkway Akron, Ohio 44333
330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947



ELASTOMERS
-SBR-

TAIPOL® SBR 1502

DESCRIPTION:

Taipol SBR 1502 is an emulsion styrene-butadiene rubber produced by cold polymerization using a mixture of rosin acid and fatty acid soaps as emulsifiers and is stabilized by a non-staining antioxidant. SBR 1502 exhibits excellent tensile strength, abrasion resistance, good mechanical properties, and good resistance to polar solvents, dilute acids and bases.

TYPICAL PROPERTIES:

| | |
|---|--------------|
| Raw Polymer Mooney Viscosity (ML 1+4, 100° C) | 52±6 |
| Bound Styrene wt % | 23.5±1 |
| Stabilizer | non-staining |
| Ash Content wt. % | 0.75 max |

APPLICATIONS:

Taipol SBR 1502 finds use in white sidewall tires, footwear, light and dark color mechanical goods and other rubber applications.

PACKAGING: 77 lb. (35 kg) bales.

STORAGE:

Store in original packaging away from direct sunlight, in a dry area (20°C-30°C) having proper ventilation.

gpb 8/16
t-Taipol SBR 1502

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.