



## MINERAL FILLERS -ADDITIONAL-

3770 Embassy Parkway, Akron, Ohio 44333  
330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

### MANSIL® ZX

#### DESCRIPTION:

Mansil® ZX is a precipitated, synthetic sodium aluminum silicate. ZX is a semi-reinforcing filler for use in all types of elastomeric compounds to provide a broad range of properties. Mansil® ZX exhibits excellent process features for extruded and molded articles.

#### TYPICAL PROPERTIES:

<i>Mansil ZX</i>	<i>Typical Range</i>
Average particle size, $\mu$	7.0 max
pH	10.0-11.5
Surface area (BET), m <sup>2</sup> /gm.	70
Specific Gravity	1.95-2.20
Moisture (2 hrs. @ 105°C), %	5.0 max
Oil Absorption (Linseed), cc/100 gms.	120
Sieve Residue (325 mesh), %	0.10 max
Sodium Sulfate, %	2.50

#### APPLICATIONS:

Mansil® ZX offers unique processing characteristics for finished articles as a mid-range filler. Mansil® ZX serves as a semi-reinforcing filler with moderate abrasion resistance and good processing properties at a suitable price point. Mansil® ZX works well in the production of extruded goods, where surface smoothness is required. In addition, the high whiteness value of Mansil® ZX is ideal for non-black articles. The typical dosage range is from 10 to 150 phr. The ability of Mansil® ZX to absorb large quantities of process oils, cause it to be the product of choice for highly extended EPDM compounds. This characteristic causes Mansil® ZX to serve as an essential formulating asset in the polymer chemist's tool belt. In addition, Mansil® ZX is typically paired in concert with many of the other commonly utilized extender materials.

*Mansil® ZX is a registered trade name of GMGBC*

T- Mansil® ZX (57963)  
TLM 8-2-2018

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.