

# RUBBER CHEMICALS -ANTIOXIDANTSNON-STAINING

# ANTIOXIDANT TNPP-HP

$$P \stackrel{R}{\longleftarrow} R \qquad R = --O \stackrel{\longleftarrow}{\longleftarrow} C_9 H_{19}$$

## **DESCRIPTION:**

Antioxidant TNPP-HP is a premium non-discoloring, non-staining phosphite antioxidant (chemically, trisnonylphenyl phosphite). It provides excellent low discoloration and high hydrolysis resistance in white and light-colored elastomeric compounds including cements and hot melts. Antioxidant TNPP-HP is also used as a stabilizer in thermoplastics like ABS, HIPS, polycarbonate, polyolefins, polystyrene, and PVC. (CAS No.: 26523-78-4)

### **TYPICAL PROPERTIES:**

| Appearance             | . clear liquid |
|------------------------|----------------|
| %Free Nonylphenol      | .0.1max        |
| Specific Gravity @25°C | .0.99          |
| Density, lb/gal        | . 8.2          |
| Viscosity, cps@25°C    | .7,800         |
| Acid Number (mg KOH/g) | .0.1 max       |

### **APPLICATIONS:**

Antioxidant TNPP-HP is known for its excellent color and non-tinting properties. It is often used in combination with phenolic antioxidants or thioesters in light colored NR and synthetic elastomers. In many polymers, Antioxidant TNPP-HP provides a chelating or sequestering effect on heavy metals preventing yellowing. It also has clearance under FDA regulation 177.2600. Normal dosages range from 0.50 to 2.0 parts on the rubber hydrocarbon and have no deleterious affect on the rate of cure or physical properties. In plastics, Antioxidant TNPP-HP is recommended at a loading of 0.2% - 1.00%. To obtain the best synergistic effect with phenolic antioxidants, add 0.2% Antioxidant TNPP-HP in addition to the phenol antioxidant loading.

gpb 12/07 t-antioxidant TNPP-HP