LOWINOX[™] AH25 stabilizer

Phenolic Antioxidant



Description

LOWINOXTM **AH25 stabilizer** is an excellent performing stabilizer based on sterically hindered dihydroxybenzene.

Chemical Name

2,5-Di-tert-amyl-hydrochinon

CAS-Number:

79-74-3

EINECS-Number:

201-222-2

Formula

LOWINOX™ AH25 stabilizer

Typical physical properties of LOWINOX[™] AH25 stabilizer

Appearance	White to cream colored powder	
Molecular weight [g/mol]	250	
Melting point (capillary) °C	179	
Bulk density [kg/m³]	290	
Volatility (2g/2h/80°C) Max %	0.5	
Ash content (5g/800°C) Max %	0.1	

SI Group Inc., 2750 Balltown Road, Schenectady, NY 12309 PH: +1 518.347.4200 www.siigroup.com

Page 1 of 2

The foregoing product brand is a trademark of one or more SI Group, Inc. affiliated companies. SI Group, The Substance Inside and the SI Group logo are Reg. U.S. Pat. & Tm Off. and additional countries, to SI Group, Inc.

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of SI Group, Inc. and its affiliated companies to ensure the accuracy or reliability of the information. Customers should contact SI Group account representatives for current information. It is the responsibility of the user to comply with all applicable laws and regulations relating to use of the product and to provide for a safe workplace. The user should consider all information contained herein only as a guide, and should take precautions that the user considers necessary or prudent to promote a safe work environment, such as considering all applicable health and safety hazards, developing safe work practice procedures and properly instructing employees, and reviewing the Safety Data Sheet (SDS) and product label for safety information.



Solubility (g/100g solvent) @ 25°C

Water	<0.1	<i>n</i> -Hexane	<0.1
Acetone	50	Chloroform	3
Diethyl ether	130	Methanol	>100
Ethanol	68	Ethyl Acetate	82
Toluene	3		

Thermogravimetric Analysis (10 mg @ 10°C/minute under N₂)

Weight Loss [%]	5	10	25
Temperature [°C]	158	177	188

Applications

LOWINOX[™] AH25 stabilizer exhibits excellent protection against oxygen and sun crack. It is recommended for unvulcanized rubber adhesives, tapes and films. LOWINOX[™] AH25 stabilizer prevents the loss of tack of unvulcanized rubber and reduces the cold flow. LOWINOX[™] AH25 stabilizer provides good scorch resistance in wire and cable applications. LOWINOX[™] AH25 stabilizer is effective in a variety of coatings such as unsaturated paint resins where it prevents skinning through oxygen inhibition. LOWINOX[™] AH25 stabilizer is also particularly useful for stabilizing acrylonitrile-based polymers.

Food Contact

For details please contact SI Group Regulatory Affairs.

Handling and Storage

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling. Store the product in a cool, dry, well-ventilated area away from incompatible materials. Unless otherwise stated, the shelf life of the product is 4 years when it is properly stored.

For additional handling and toxicological information consult the SI Group Material Safety Data Sheet.