



3770 Embassy Parkway Akron, Ohio 44333
 330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

ZINC PRODUCTS
-ZINC OXIDES-

ZINC OXIDE XFT-MA

PRODUCT DESCRIPTION:

Zinc Oxide XFT-MA is a French Process Zinc Oxide made from high purity zinc metal and coated with propionic acid to aid dispersion in rubber.

USES:

Zinc Oxide XFT-MA is a fine particle size oxide serving as a cure activator/additive in rubber compounding, adhesives and latex applications. Being French process zinc, it can be used in white and colored rubber articles, where a zinc oxide of good color and high chemical purity is desirable. Its finer particle size and increased surface area contribute to increased activation of cures, especially in latex applications. The high heat transfer ability of ZnO means it is useful in dynamic applications where internal heat buildup is a problem. 10 phr or more of ZnO will transfer heat from the center of a product to the surface where it can be dissipated. Conversely, non-black compounds heat up quicker and more evenly during cure if higher levels of ZnO are used. Useful in non-black articles to protect from UV weathering. It is more effective than TiO₂. Use approximately 10% ZnO (not 10 phr) for good UV protection in non-black formulas.

TYPICAL ANALYSIS:

Chemical (%):

ZnO (Dry Basis)	99.9
Pb	0.003
Cd.....	0.001
Fe	nil
Cu.....	nil
Propionic Acid	0.02

Physical:

Surface Area	9.0 m ² /g
Mean Particle Size	0.12 microns
Specific Gravity	5.6 g/ml
Passing 325 mesh.....	99.9%

gpb
 12/14, t-xft-ma.doc

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.